

(12) International Application Status Report

Received at International Bureau: 15 November 2019 (15.11.2019)

Information valid as of: 08 May 2020 (08.05.2020)

Report generated on: 30 September 2020 (30.09.2020)

(10) Publication number:

WO2020/111562

(43) Publication date:

04 June 2020 (04.06.2020)

(26) Publication language:

Korean (KO)

(21) Application Number:

PCT/KR2019/015021

(22) Filing Date:

07 November 2019 (07.11.2019)

(25) Filing language:

Korean (KO)

(31) Priority number(s):

10-2018-0148373 (KR)

(31) Priority date(s):

27 November 2018 (27.11.2018)

(31) Priority status:

Priority document received (in compliance with PCT Rule 17.1)

(51) International Patent Classification:

B23K 35/02 (2006.01); **B23K 35/30** (2006.01); **C22C 19/05** (2006.01); **B22F 9/08** (2006.01)

(71) Applicant(s):

POONGSAN HOLDINGS CORPORATION [KR/KR]; 156, Anaji-ro Gyeong-gu, Incheon 21106 (KR) *(for all designated states)*

(72) Inventor(s):

KIM, Daehyun; (Ballim-dong, Lucky Ballim Apt) 13-207, 105, Bansong-ro Seongsan-gu, Changwon-si, Gyeongsangnam-do 51424 (KR)

LEE, Jihoon; (Gwandong-dong, Palpan Village Buyeong e-greentown 3-cha Apt) 306-102, 68, Deokjeong-ro Gimhae-si, Gyeongsangnam-do 50998 (KR)

SONG, Jungik; (Seongju-dong, Hallym Prugio) 104-2001, 13, Oeri-ro 34beon-gil Seongsan-gu, Changwon-si, Gyeongsangnam-do 51471 (KR)

CHO, Yunju; (Dongsam-dong, Gongwon Villa 3-cha) 301, 26, Araetseobal-gil 21beon-gil Yeongdo-gu, Busan 49126 (KR)

(74) Agent(s):

KBK & ASSOCIATES; (Jamsil Hyundai Building 7th Floor) 82, Olympic-ro, Songpa-gu Seoul 05556 (KR)

(54) Title (EN): BRAZING NI-CR-FE-P-BASED ALLOY POWDER HAVING LOW MELTING POINT AND HIGH CORROSIVE RESISTANCE AND MANUFACTURING METHOD THEREFOR

(54) Title (FR): POUDRE D'ALLIAGE À BASE DE NI-CR-FE-P POUR BRASAGE AYANT UN POINT DE FUSION BAS ET UNE RÉSISTANCE À LA CORROSION ÉLEVÉE, ET SON PROCÉDÉ DE FABRICATION

(54) Title (KO): 저용점 및 고내식성을 갖는 NI-CR-FE-P계 브레이징용 합금분말 및 이의 제조 방법

(57) Abstract:

(EN): The present invention relates to a brazing Ni-Cr-Fe-P-based alloy powder having a low melting point and high corrosive resistance and a manufacturing method therefor and, more specifically, to a brazing Ni-Cr-Fe-P-based alloy powder comprising 5 to 40 weight% of Cr, 5 to 30 weight% of Fe, 5 to 20 weight% of P, and the balance of Ni and other inevitable impurities, and a method for manufacturing a brazing Ni-Cr-Fe-P-based alloy powder having a low melting point and high corrosive resistance through a gas atomizing process in which a dissolution temperature of 1300 to 1650#, a molten metal nozzle diameter of 3 to 10 mm, and a gas spray pressure of 3 to 15 bar are set. Having a low melting point, compared to preexisting products, the alloy powder according to the present invention advantageously works at joining temperatures in a post-treatment process. When used in brazing, the alloy powder can find various applications as a high functional joining material.

(FR): La présente invention concerne une poudre d'alliage à base de Ni-Cr-Fe-P pour brasage ayant un point de fusion bas et une résistance à la corrosion élevée et son procédé de fabrication et, plus spécifiquement, une poudre d'alliage à base de Ni-Cr-Fe-P pour brasage comprenant de 5 à 40 % massiques de Cr, de 5 à 30 % massiques de Fe, de 5 à 20 % massiques de P et le reste de Ni et d'autres impuretés inévitables, et un procédé de fabrication d'une poudre d'alliage à base de Ni-Cr-Fe-P pour brasage ayant un point de fusion bas et une résistance à la corrosion élevée par le biais d'un procédé d'atomisation de gaz dans lequel sont réglés une température de dissolution allant de 1300 à 1650 °C, un diamètre de buse de métal fondu allant de 3 à 10 mm et une pression de pulvérisation de gaz allant de 3 à 15 bars. Ayant un point de fusion bas en comparaison des produits préexistants,

la poudre d'alliage selon la présente invention fonctionne avantageusement à des températures de jonction dans un processus de post-traitement. Lorsqu'elle est utilisée en brasage, la poudre d'alliage peut trouver diverses applications en tant que matériau d'assemblage hautement fonctionnel.

(KO): 본 발명은 저용점 및 고내식성을 갖는 Ni-Cr-Fe-P계 브레이징용 합금분말 및 이의 제조 방법에 관한 것으로서, 보다 구체적으로는 5 내지 40 중량%의 Cr, 5 내지 30 중량%의 Fe, 5 내지 20 중량%의 P, 잔부인 Ni 및 기타 불가피한 불순물을 포함하는 Ni-Cr-Fe-P계 브레이징용 합금분말 및 가스 아토마이징(Gas atomizing) 공정을 통한 Ni-Cr-Fe-P계 브레이징용 합금분말의 제조방법으로, 용해온도는 1300 내지 1650 °C이며, 용탕노즐구경은 3 내지 10 mm이고, 가스분사압력은 3 내지 15 bar인 저용점 및 고내식성을 갖는 Ni-Cr-Fe-P계 브레이징용 합금분말의 제조방법에 관한 것이다. 본 발명에 따른 합금분말은 기존제품 대비 저용점을 가짐으로써 후처리 공정에서 접합 온도에 유리하게 작용하며, 브레이징에 적용함으로써 고기능성 접합재로서의 다양한 활용이 가능하다.

International search report:

Received at International Bureau: 20 February 2020 (20.02.2020) [KR]

International Report on Patentability (IPRP) Chapter II of the PCT:

Not available

(81) Designated States:

AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW

European Patent Office (EPO) : AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR

African Intellectual Property Organization (OAPI) : BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG

African Regional Intellectual Property Organization (ARIPO) : BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW

Eurasian Patent Organization (EAPO) : AM, AZ, BY, KG, KZ, RU, TJ, TM