

Tabelle 1: Zusammensetzung der Lackformulierungen

Lackformulierung	F1	F2	F3	F4	F5	F6	F7	F8	F9
Bestandteile (Gewichtsteile)									
PESA 1	20.0	-	-	-	-	-	-	-	-
PEA 1	41.5	-	-	-	-	-	-	-	-
UA 1	-	20.0	-	-	-	-	-	-	-
PESA 2	-	41.5	-	-	-	-	-	-	-
EA 1	-	-	60.0	80.0	60.0	80.0	100.0	-	-
UA 2	-	-	40.0	20.0	40.0	20.0	-	-	-
EA 2	-	-	-	-	-	-	-	100.0	95.0
Inertharz	-	-	-	-	-	-	-	-	5.0
PEA 2	10.0	10.0	-	-	-	-	-	-	-
DPGDA	14.5	14.5	-	-	-	-	-	-	-
TBCH	10.0	10.0	-	-	-	-	-	-	-
Mattierungsmittel	3.0	3.0	-	-	0.75	0.75	0.75	0.75	0.75
Mikronisierter Kaolin	-	-	-	-	0.75	0.75	0.75	0.75	0.75
Mikronisiertes Wachs	0.3	0.3	-	-	-	-	-	-	-
Fotoinitiator 1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Fotoinitiator 2	0.2	0.2	-	-	-	-	-	-	-